

# ETERNITY COLLECTION

## EUROPEAN STANDARD

**NORMATIVE EN 13227**

- SELECT ●
- NATURE △
- RUSTIC ■
- FREE CLASS
- MIX 1
- MIX 2



The mark of responsible forestry



Classification for hardwoods

Face of the element			
FEATURES	●	△	■
<b>Sound sapwood</b>	Not permitted	Permitted	Slight traces permitted
<b>Knots</b>			
Sound and intergrown	Permitted if: diameter ≤2 mm if not grouped together*	Permitted if: diameter ≤5 mm if not grouped together*	All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring
Unsound knots	Permitted if: diameter ≤1 mm if not grouped together*	Permitted if: diameter ≤2 mm if not grouped together	
<b>Checks</b>	Not permitted	Not through going. Permitted in the width ≤0,5 % of the width of the element	
<b>Bark pockets</b>	Not permitted	Not permitted	
<b>Lightning shake</b>	Not permitted	Not permitted	
<b>Slope of grain</b>	Permitted, no limit	Permitted, no limit	
<b>Colour variation</b>	Permitted. Slight traces of natural discoloration (mineral lines) permitted	Permitted	
<b>Medullary ray</b>	Permitted	Permitted	
<b>Biodeterioration</b>	Not permitted	Not permitted	Not permitted, except blue stain and black holes
Non-visible parts			
All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring. In class ● sound sapwood permitted if in a corner and up to 50% of the thickness of the elements.			
* Knots are grouped together if the distance separating them, measured from edge to edge, does not exceed 30 mm.			

# ETERNITY COLLECTION

## EUROPEAN STANDARD

**NORMATIVE EN 13226**  
WITH GROOVES  
AND/OR TONGUES

SELECT ●  
NATURE ▲  
RUSTIC ■  
FREE CLASS  
MIX 1  
MIX 2



The mark of responsible forestry



Classification for hardwoods

Face of the element			
FEATURES	●	▲	■
Sound sapwood	Not permitted	Permitted	Slight traces permitted
Knots			
Sound and intergrown	Permitted if: diameter ≤2 mm if not grouped together*	Permitted if: diameter ≤5 mm if not grouped together*	
Unsound knots	Permitted if: diameter ≤1 mm if not grouped together*	Permitted if: diameter ≤2 mm if not grouped together	All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring
Checks	Not permitted	Not through going. Permitted in the width ≤0,5 % of the width of the element	
Bark pockets	Not permitted	Not permitted	
Lightning shake	Not permitted	Not permitted	
Slope of grain	Permitted, no limit	Permitted, no limit	
Colour variation	Permitted. Slight traces of natural discoloration (mineral lines) permitted	Permitted	
Medullary ray	Permitted	Permitted	
Biodeterioration	Not permitted	Not permitted	Not permitted, except blue stain and black holes
Non-visible parts			
All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring. In class ● sound sapwood permitted if in a corner and up to 50% of the thickness of the elements.			
* Knots are grouped together if the distance separating them, measured from edge to edge, does not exceed 30 mm.			