

Roseroood Roseroood



Stemau





Wood species: **ROSEWOOD**



Wood Flooring Production

Stemau S.r.l.

Legal Head Office and Showroom Via Pieve Ligure, 15 00168 Rome
Warehouse and Showroom Via Refrancore, 26 00166 Rome
Factory Via Morsasco, 41 00166 Rome
Phone 0639.06.45.50.22.60 - info@stemausr.it - www.stemausr.it
VAT 01814361000 - Fiscal Code 07578980588

INFORMATION SHEET In compliance with the provisions of the law Legislative Decree no. 206/2005 "Regulations for consumer information"

EUROPEAN STANDARDS: UNI EN 13489

COMMERCIAL NAME: ROSEWOOD

BOTANICAL NAME: DALBERGIA NIGRA

FAMILY: LEGUMINOSAE PAPILIONACEAE

ORIGIN: ASIA

OXIDATION: LOW

HARDNESS: HIGH

DENSITY: FRESH 1000-1100 Kg/m³ - DRY 800-900 Kg/m³

DRYING: SLOW TO AVOID CRACKS AND DEFORMATIONS

GROWTH AREA: INDIA - THAILAND - INDONESIA

COLOUR: DARK, BROWN TENDING TOWARDS REDDISH

PROPERTY: STURDY, RESISTANT, DURABLE, STABLE, EASILY WORKABLE WOOD

SELECT ROSEWOOD



- SELECT**  **UNIFORM TONES, HOMOGENEOUS VEININGS, RANDOM SMALL KNOTS**
NATURE  **SLIGHT CHROMATIC SHADES, ACCENTUATED VEININGS, CONTAINED KNOTS**
RUSTIC  **MARKED TONE CHANGES, STRONG VEININGS, VISIBLE KNOTS AND CRACKS**

Technical specifications of ROSEWOOD 2 or 3 Layers Pre-finished Parquet

ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Density kg/m ³	800-900	
Nominal upper layer thickness mm	3/4	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,16	UNI EN 14342-2013

QUICK INSTALLATION GUIDE

2 Layers Laying: with glue or floating (only for planks from width of 120 mm and above).

3 Layers Laying: Floating

It is recommend using solvent-free glues to avoid stains on the surface.

For floating laying, it is recommend using a shock-absorbing or insulating mat.

Installation on underfloor heating: suitable (if the conditions of the system allow for it and comply with the regulations).

