

REGULATION NORMA UNI EN 13489

СЕЛЕКТ ●
 НАТУР △
 РУСТИК ■
 СВОБОДНЫЙ
 КЛАСС
 КЛАСС МИКС 1
 КЛАСС МИКС 2



Face of the element				
ХАРАКТЕРИСТИКИ	●	△	■	
Sound sapwood or heartwood*	Not permitted Not permitted	Permitted Permitted up to 50% of the face, if distributed	Slight traces permitted Permitted	
Knots** Sound and intergrown Unsound	Permitted if: diameter ≤2 mm if not grouped together***	Permitted if: diameter ≤5 mm if not grouped together***	All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the parquet flooring	
	Permitted if: diameter ≤1 mm if not grouped together***	Permitted if: diameter ≤2 mm if not grouped together***		
Checks	Not permitted	Not through going. Permitted if the width ≤0,5% of the width of the element		
Bark pockets	Not permitted	Not permitted		
Lightning shake	Not permitted	Not permitted		
Slope of grain	Permitted, no limit	Permitted, no limit		
Colour variation	Permitted. Slight traces of natural discoloration (mineral lines) permitted	Permitted		
Medullary ray	Permitted	Permitted		
Biodeterioration	Not permitted	Not permitted		Not permitted, except blue stain and black holes

Non-visible parts

All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring.

* Sound sapwood or "heartwood" shall be chosen depending on the wood species concerned.

** Cracks in knots and knot holes shall be filled.

*** Knots are grouped together if the distance separating them, measured from edge to edge, does not exceed 30 mm.